

KALCOR S

Zirconium Corundum

Material data sheet

Material description in general

The material KALCOR S is a zirconium corundum, which has a high abrasion resistance and was developed for an excellent thermal shock resistance and temperature resistance. KALCOR S is formed into tiles, shaped components and cylinders. This shape capability allows KALCOR S to be manufactured into many different components demanded by various industries.

Material properties

Feature	Unit	Data
Chemical composition	Wt.-% $\text{Al}_2\text{O}_3 + \text{ZrO}_2$	79 - 83
	Wt.-% SiO_2	12 - 16
Hardness	Vickers HV1	850
Density	g/cm^3	≥ 3.05
	lb/ft^3	≥ 190.40
Open porosity	%	< 18
Thermal coefficient of expansion	K^{-1} (20 - 1000 °C)	6.5×10^{-6}
	$^{\circ}\text{F}^{-1}$ (68 - 1832 °F)	3.61×10^{-6}
Thermal conductivity	W/mK (20 - 1000 °C)	4.2
	$\text{Btu inch/ft}^2\text{h}$ (68 - 1832 °F)	29.14
Max. application temperature	°C	1200
	°F	2192
Max. thermal shock resistance	K/h	300
	F°/h	572
Wear resistance acc. ASTM C704-15	cm^3 with 90°	≤ 2.3

Approximate figures are given for all technical data. They are based on assessment of tests on specific samples and cannot be considered as a guarantee for which Kalenborn would have to assume legal responsibility. Subject to technical changes and errors.

KALCOR S

Zirconium Corundum

Material data sheet

Installation

- Cylinders or shaped components in cement mortar or special setting compounds
- Mechanical fixing is also possible

Advantages

- High abrasion resistance
- High temperature resistance
- Excellent thermal shock resistance
- High chemical resistance

Applications from energy and the environment, cement and building materials, iron and steel, mining and other industries

centrifuges and driers

chain and screw conveyors

chutes and hoppers

cyclones

diverter

drying drums

immersion pipes

mixers

nozzles

pipes and bends

separators

separators, fans

skip collecting bins

skips and skip chutes

supply channels

venturis

Due to the manufacturing process, it is not possible to exclude small variations in the properties of the product. This affects tolerances in the size, outer appearance and surface finish. Included are some typical features of mineral/ceramic materials, such as spalling, porosity and hairline cracks, all of which can be present within the range of specified tolerances.

